

CABMER LL 2002-NL

Product Information

1. Product Description

CABMER LL 2002 is a linear low density polyethylene compound for jacket and general solid insulation. CABMER LL 2002 combines good processability at very high extrusion speed. The combination of CABMER LL 2002 is stabilized compound in order to retain maximum mechanical properties and resistance to heat deformation.

2. Specifications

ASTM D1248 Type I, Class A, Category 4, Grade E4, E5

3. Physical Properties

Properties	Test Method	Value	Units
Physical			
Melt flow rate 190 °C, 2.16 kg	ISO 1133	0,5	g/10 min
Conventional density	ISO 1183 Method D	920	Kg/m ³
Vicat softening temperature	ISO 306 Method A	102	°C
Shore hardness D	ISO 868	52	-
Tensile strength @ yield	ISO 527-2	15	MPa
Tensile strength @ break	ISO 527-2	45	Mpa
Elongation @ break	ISO 527-2	>750	%
ESCR (F50)	ASTM D 1653	>5000	Hour
Electrical			
Volume Resistivity	IEC 60093	1,00	e+6 ohm-cm
Dielectric Constant @1Hz	ASTM D 1531	2,28	-
Dissipation factor @1Hz	ASTM D 1531	100	µrad

4. Processing Data

The good processing characteristics of CABMER LL 2002 allow wide latitude of both equipment and process conditions. Normally the extruder barrel temperatures should be set to give a resulting melt temperature in the range of 200 -220 °C. Processing above 250 °C should be avoid to prevent heat degradation.

5. Packaging :

CABMER LL 2002 is sold in pallet form and is available in the 25 kg bags and 500/600 kg bigbag.