



TECHNICAL DATA SHEET

Product Name

SCG HDPE

Product Type

Natural HDPE for Solid Insulation

Product Grade

H512W

Product Description

SCG HDPE H512W is a high density polyethylene for solid insulation in cable application. It is also suitable for outer skin in “foam-skin” constructions. It provides good performance across the full range of telecommunication insulation applications, including aircore and petroleum jelly filled cable designs in both buried and aerial environments.

Typical Application

- Solid insulation of communication cable

Product Characteristics

- Long-term insulation stability performance
- Good mechanical properties
- High extrusion speed

International Compliance

- ASTM D 1248 Type III, Class A, Category 3, Grade E8, E9*
- ISO 1872-PE, KHKN, 50-D006*

* New HDPE resin for insulation meets the following raw materials specifications

**Cable insulated with New HDPE resin for insulation using sound commercial extrusion practices and testing procedures, should meet the following cable specifications.

Physical Properties

Property	Test Method	Typical Value	Unit
Melt Flow Rate	ASTM D 1238 @ 190 °C, 2.16 kg	1.1	g/10 min
Density (Base resin)	ASTM D 1505	0.953	g/cm ³
Tensile Strength at Break	ASTM D 638 @ speed 50 mm/min	30	MPa
Elongation at Break	ASTM D 638 @ speed 50 mm/min	>600	%
Hardness	ASTM D 2240	63	Shore D
ESCR (50°C, 10% Igepal, F0)	ASTM D 1693	>1000	Hrs
Dielectric Constant, 1 MHz	ASTM D 1531	2.1	-
Dissipation Factor, 1 MHz	ASTM D 1531	0.00077	-
DC Volume Resistivity	ASTM D 257	10 ¹⁶	ohm.cm
Dielectric Strength	ASTM D149	40	kV/mm

Note: the given values are typical value measured on the product. Values herein are not to be constructed as a product specification.

Processing Guidelines

SCG Performance Chemicals Co., Ltd.

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand

Tel.: +66 2586 1111 ext. 3905 Fax: +66 2586 3676

Email: wire&cable@scg.com



TECHNICAL DATA SHEET

Product Name

SCG HDPE

Product Type

Natural HDPE for Solid Insulation

Product Grade

H512W

For extrusion of SCG HDPE H512W, It is recommended to use with the screw giving good homogenization without excessive shear. Standard PE screws have proven satisfactorily which provide good result. Recommended melt temperature is 220-280 °C using conductor preheats ranging from 110-140 °C

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Natural pellet

Product Packaging

- 25 kg loose bag
- 25 kg bag on pallet
- 750 kg big bag

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/ Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50°C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

Recycling

SCG Performance Chemicals Co., Ltd.

1 Siam Cement Road, Bangsue, Bangkok, 10800 Thailand

Tel.: +66 2586 1111 ext. 3905 Fax: +66 2586 3676

Email: wire&cable@scg.com



TECHNICAL DATA SHEET

Product Name

SCG HDPE

Product Type

Natural HDPE for Solid Insulation

Product Grade

H512W

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

Related Documents

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.
 - Material Safety Datasheet
 - Statement on compliance to food contact regulations

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.